## Amendments to the Claims

This listing of claims will replace all prior listings of claims in the application.

## Listing of Claims

- 1. (Original) An aqueous aluminum brazing composition which comprises a zinc-based flux, an organic binder, and (meth)acrylic acid/(meth)acrylate copolymer emulsion as a precipitation inhibitor in an amount of 0.03-1.50 wt% of 100 wt% of the brazing composition, the brazing composition having a thixotropic index calculated by dividing a logarithm of viscosity of the brazing composition measured at 25°C and 10 rpm by a logarithm of viscosity of the brazing composition measured at 25°C and 100 rpm by using an EH-type viscometer of 1.01-1.20.
- 2. (Original) The brazing composition according to claim 1, wherein the zinc-based flux is a K-Zn-F-type zinc fluoride.
- 3. (Currently Amended) The brazing composition according to claim 1-or-2, further comprising metal silicon powder as a brazing filler metal.
- 4. (Currently Amended) The brazing composition according to any of claims 1 to 3 claim 1, further comprising a reaction inhibitor which inhibits a reaction between zinc and a carboxyl group in the organic binder or the precipitation inhibitor.

- 5. (Original) The brazing composition according to claim 4, wherein the reaction inhibitor is an amino alcohol having a boiling point of  $120-200^{\circ}$ C.
- 6. (Currently Amended) An aluminum material coated with a brazing composition which is produced by applying the brazing composition according to any of claims 1 to 5claim 1 to the aluminum material and drying the brazing composition, thereby causing a dried residual component in the brazing composition to adhere to a surface of the aluminum material.
- 7. (Original) The aluminum material according to claim 6, wherein an average thickness and a maximum thickness of a film of the brazing composition are respectively 2-15  $\mu m$  and 30  $\mu m$  or less.
- 8. (Currently Amended) The aluminum material according to claim 6-or-7, wherein an average particle diameter of the zinc-based flux is 30  $\mu m$  or less.
- 9. (Currently Amended) An aluminum brazing method comprising assembling the aluminum material according to any of claims 6 to 8 claim 6 into a specific structure, and heating the structure to a brazing temperature to form a zinc diffusion layer on the surface of the aluminum material.
- 10. (Original) An automotive heat exchanger manufactured by using the brazing method according to claim 9.